



比翼实业有限公司
T&T Industry Group Ltd
星天化实业（深圳）有限公司
Galaxy Chemical Technology Co Ltd
惠州市百川新材料科技有限公司
Huizhou Oceanpower Technology Ltd

R612, Huafeng Yu'an Commercial Building, Baoan 45th District, Shenzhen, China

Features: Super high flowability(超高流动); Low order(低气味); Without DTBP, BIBP (不含DTBP, BIBP)

Applications: Melt-blown nonwoven(熔喷无纺布); Medical mask(口罩); Protective clothing(防护服)

PP RP-M1500

性能	Properties	测试标准 Test Standard	测试条件 Test Condition	国际单位 S.I.Units	典型值 Typical Value
熔体流动速率	Melt-Flow Rate	GB/T3682	230°C/ 2.16KG	g/10min	1500
熔点	Melting Point	DSC	10°C/min	°C	165
分子量分布	Molecular weight distribution	GPC	150°C	/	<3
灰分	ASH	GB/T9345.1	800°C/2h	%	<0.01
挥发性	Volatile Constituents	GB/T2914	/	%	<0.05
二叔丁基过氧化物 DTBP残留量	DTBP	GB/T30923	/	<5mg/kg	w/o
1,4-双叔丁基过氧异 丙基苯BIBP	BIBP				w/o

* 以上数值为典型值，仅供客户参考使用，不作为品质指标最低值或最高值的保证及其他任何用途的保证。

* The above values are typical values, for customer reference only, not as a guarantee of the lowest or highest value of index or any other purpose.